

GB 1460864

JAN 1977

GROUP 351
CLASS 285
RECORDED

ICATION

1460864

1460864

- (21) Application No. 11308/74 (22) Filed 14 March 1974
(23) Complete Specification filed 13 June 1975
(44) Complete Specification published 6 Jan. 1977
(51) INT CL' F16L 19/00
(52) Index at acceptance F2G 25A 2B
(72) Inventors JACK BEACHAM and BRIAN BERNARD DEELEY

GREAT BRITAIN (19)
GROUP 351
CLASS 285
RECORDED




(54) IMPROVEMENTS IN PIPE UNIONS

(71) PANY LII
Delta Road
hereby dec
pray that a
the method
be particu
following s
This inve
10 providing
first and set
which the
more partic
comprising
flange and
member hi
adjacent to
being adap
with the fir
20 of the tub

SPEY Q67 *A1007Y/01 *GB 1460-864
Mfg. pipe union for incompatible threaded members - by threading
tubular member, fitting union nut, screwing end member on and
deforming threaded joint
SPERRYN & CO LTD 14.03.74-GB-011308
(06.01.77) F16L 19

A pipe union for two incompatible threaded members is
formed from a stamped union nut (1) held captive on a sta-
mped and machined tubular member (2) secured to a forged member (3).
The nut is tapped and the member (3) has an external tapered thread (6).
The union is formed by first forming a thread on one end of the tubular member (2) and then passing the nut over this end. The member (3) is
then screwed onto the tubular member and a ball plunger or roller bur-
nishing tool inserted to expand the joint to bind the threads of the joint together to form a gas
tight seal. 13.6.75 (4pp)



member by co-operation between the
flanges of the nut and the tubular
member on tightening of the union
nut onto the first member, and a
25 further metallic member secured to the
other end of the tubular member and
adapted to screw-threadedly engage with
the second screw-threaded member, the
union nut being held captive on the tubular
30 member by the flange on the tubular
member and said further member which has
a sufficiently large transverse dimension to
prevent passage of the union nut over said
further member.
35 Unions of this kind have been used for
connecting gas appliances together, for
connecting a meter service governor to a
meter for example.
It is known to connect the tubular member
40 to said further member after assembly of the
union nut onto the tubular member by
screwing and brazing the tubular member to
said further member.
This is, however, an expensive operation,
45 requires testing of the seal between the two
members, and has a high reject rate.
Moreover the seal between the two
members may be broken when the union is

tion of the 50
method of
and set forth
end of the
er member
threads, 55
the tubular
other end,
er to said
permanently
int between 60
aid further
radially.
the further
a drop of a
applied to 65
per at said
other end is formed with an external screw
thread for engagement with a co-operating
internal screw thread formed in said further
70 member.
Usually the further member will be
formed with an external radially extending
polygonal flange for engagement by a
spanner when the further member is
75 tightened in use to the second member. It is
this polygonal flange which would prevent
assembly of the union nut onto the tubular
member if the tubular member were to be
80 made integral with the further member.
The tubular member and the further
member may be made of any suitable metal
but preferably they are made of brass.
The expansion of the joint between the
tubular member and the further member is
85 conveniently performed by cold forming
with a ball plunger or roller burnishing tool.
The invention will now be further
described, by way of example only, with
reference to the accompanying drawing
90 which is an axial cross section of a com-
pleted brass union adapted to secure an
externally screw-threaded first member to an
internally screw-threaded second
member to provide fluid communication
95 therebetween.

The union comprises a stamped union nut 1 held captive on a stamped and machined tubular member 2 secured to a further member 3 which is a forging.

5 The union nut 1 is internally screw-threaded for engagement with external screw threads on a first member, not shown, and is provided with an internal radial flange 4 for engagement with an external radial
10 flange 5 which is an integral part of one end of the tubular member 2. When the union nut 1 is screwed in use onto the first member the tubular member 2 is drawn towards the first member by the engagement between
15 the flanges 4 and 5.

The further member 3 is formed with an external tapered screw thread 6 for engagement with an internal co-operating screw thread of a second member, not
20 shown, and is provided with an integral polygonal radial flange 7 for engagement by a spanner during tightening in use of the further member 7 to the second member.

Initially the other end 8 of the tubular member 3 comprises a plain sleeve. Prior to assembly of the union nut 1 onto the sleeve the exterior of said other end 8 is formed
25 with a plain external screw thread for engagement with a complementary screw thread formed internally of the further member 3. The union nut is then assembled onto the tubular member 2 by passing it over
30 said other end 8 of the tubular member. The tubular member and the further member are then screwed together and a ball plunger or roller burnishing tool is inserted into the joint between the members by passing it
35 through the further member 3, and the joint between the members is expanded radially over the distance A by cold forming to increase the internal diameter D of the joint and to bind the screw threads of the joint together to form a gas-tight seal between the
40 tubular member 2 and the further member 3.

45 In one example the initial diameter D is 0.875 inches and a plunging tool of 0.925" diameter is used. The diameter D is thus increased by slightly more than 4% of its initial value.

50 In order to increase the break-loose torque of the joint between the members 2 and 3 a drop of a screw-thread locking material such as that sold under the Registered Trade Mark 'LOCTITE'
55 STULOCK (OR GRADE 75) is applied to the middle part of one of the screw threads before the members 2 and 3 are screwed together.

WHAT WE CLAIM IS:—

1. A method of manufacturing a pipe union of the kind set forth comprising forming said other end of the tubular member and said further member with complementary screw threads, assembling
60 the union nut onto the tubular member by passing it over said other end of the tubular members, screwing said tubular member to said further member, and then permanently deforming the screw-threaded joint between said
65 tubular member and said further member by expanding the joint radially.

2. The method according to claim 1 in which the tubular member is formed with its screw thread prior to assembling the union
70 nut onto the tubular member.

3. The method according to claim 1 or claim 2 in which prior to screwing the tubular member to said further member screw-thread locking material is applied to at least
75 one of the co-operating screw threads.

4. The method according to any of the preceding claims in which the co-operating screw threads comprise an external screw thread formed on the tubular member and an internal screw thread formed on said
80 further member.

5. The method according to any of the preceding claims in which the expansion of the joint is performed by cold forming.

6. The method according to claim 5 in which the joint between the tubular member is expanded by insertion of a ball plunger.

7. The method according to claim 5 in which the joint between the tubular member is expanded by a roller burnishing tool.

8. The method according to any of the preceding claims in which the tubular member and said further member are of
85 brass.

9. The method according to any of the preceding claims in which the internal diameter of the joint between the tubular member and said further member is increased by more than four per cent of the initial diameter.

10. The method according to claim 1 and substantially as described with reference to the accompanying drawing.

11. A pipe union of the kind set forth produced by the method according to any of the preceding claims.

12. A pipe union of the kind set forth manufactured according to the method of claim 10 and substantially as described with reference to the accompanying drawing.

The union comprises a stamped union nut 1 held captive on a stamped and machined tubular member 2 secured to a further member 3 which is a forging.

- 5 The union nut 1 is internally screw-threaded for engagement with external screw threads on a first member, not shown, and is provided with an internal radial flange 4 for engagement with an external radial flange 5 which is an integral part of one end of the tubular member 2. When the union nut 1 is screwed in use onto the first member the tubular member 2 is drawn towards the first member by the engagement between the flanges 4 and 5.

- 15 The further member 3 is formed with an external tapered screw thread 6 for engagement with an internal co-operating screw thread of a second member, not shown, and is provided with an integral polygonal radial flange 7 for engagement by a spanner during tightening in use of the further member 7 to the second member.

- 20 Initially the other end 8 of the tubular member 3 comprises a plain sleeve. Prior to assembly of the union nut 1 onto the sleeve the exterior of said other end 8 is formed with a plain external screw thread for engagement with a complementary screw thread formed internally of the further member 3. The union nut is then assembled onto the tubular member 2 by passing it over said other end 8 of the tubular member. The tubular member and the further member are then screwed together and a ball plunger or roller burnishing tool is inserted into the joint between the members by passing it through the further member 3, and the joint between the members is expanded radially over the distance A by cold forming to increase the internal diameter D of the joint and to bind the screw threads of the joint together to form a gas-tight seal between the tubular member 2 and the further member 3.

- 45 In one example the initial diameter D is 0.875 inches and a plunging tool of 0.925 inch diameter is used. The diameter D is thus increased by slightly more than 4% of its initial value.

- 50 In order to increase the break-loose torque of the joint between the members 2 and 3 a drop of a screw-thread locking material such as that sold under the Registered Trade Mark 'LOCTITE' STUDLOCK (OR GRADE 75) is applied to the middle part of one of the screw threads before the members 2 and 3 are screwed together.

WHAT WE CLAIM IS:—

1. A method of manufacturing a pipe union of the kind set forth comprising forming said other end of the tubular member and said further member with complementary screw threads, assembling the union nut onto the tubular member by passing it over said other end of the tubular members, screwing said tubular member to said further member, and then permanently deforming the screw-threaded joint between said tubular member and said further member by expanding the joint radially.

2. The method according to claim 1 in which the tubular member is formed with its screw thread prior to assembling the union nut onto the tubular member.

3. The method according to claim 1 or claim 2 in which prior to screwing the tubular member to said further member screw-thread locking material is applied to at least one of the co-operating screw threads.

4. The method according to any of the preceding claims in which the co-operating screw threads comprise an external screw thread formed on the tubular member and an internal screw thread formed on said further member.

5. The method according to any of the preceding claims in which the expansion of the joint is performed by cold forming.

6. The method according to claim 5 in which the joint between the tubular member is expanded by insertion of a ball plunger.

7. The method according to claim 5 in which the joint between the tubular member is expanded by a roller burnishing tool.

8. The method according to any of the preceding claims in which the tubular member and said further member are of brass.

9. The method according to any of the preceding claims in which the internal diameter of the joint between the tubular member and said further member is increased by more than four per cent of the initial diameter.

10. The method according to claim 1 and substantially as described with reference to the accompanying drawing.

11. A pipe union of the kind set forth produced by the method according to any of the preceding claims.

12. A pipe union of the kind set forth manufactured according to the method of claim 10 and substantially as described with reference to the accompanying drawing.

BARKER, BRETTELL & DUNCAN
Chartered Patent Agents
Agents for the Applicants
138 Hagley Road
Edgbaston
Birmingham B16 9PW.

Printed for Her Majesty's Stationery Office by the Courier Press, Leamington Spa, 1977.
Published by the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from
which copies may be obtained.